

PATENT
WELDABLE
REINFORCEMENT

PU85A ultramarine blue rough, reinforced glass fiber PU

BELT
DOPRAVNÍ SYSTÉMY

Order No.	Diameter \varnothing		Cross section cm ²	approx. Weight kg/100 m	Standard Roll		Recommended Min. pulley \varnothing		Fmax/belt (Standard)*	
	mm	inch			m	ft	mm	inch	kg	lbs
FBZRP85A080R	8,0	5/16	0,500	6,0	100	328	85	3,2	19,8	43,5
FBZRP85A095R	9,5	3/8	0,710	8,5	100	328	100	3,7	28,1	61,9
FBZRP85A100R	10,0	7/16	0,785	9,4	50	164	105	3,9	31,0	68,2
FBZRP85A120R	12,0	15/32	1,130	13,5	50	164	125	4,7	44,7	98,3
FBZRP85A125R	12,5	1/2	1,230	14,8	50	164	130	4,9	48,6	107,0
FBZRP85A143R	14,3	9/16	1,605	21,0	50	164	150	5,7	63,4	139,4
FBZRP85A150R	15,0	19/32	1,770	21,5	50	164	155	5,9	69,9	153,8
FBZRP85A180R	18,0	3/4	2,54	31,0	50	164	195	7,5	-	-
FBZRP85A200R	20,0	25/32	3,14	40,0	50	164	205	7,9	-	-

approx. 88° Shore A

Recommended pretension

0,5...2 %

Coefficient of friction μ : Steel: approx. 0,45 | PE: approx. 0,30 | HDPE: approx. 0,25

* = coefficient of friction μ :0,5